

# Trends in Optics and Photonics

TOPS Volume I

DISTRIBUTION STATEMENT A

Approved for public release;

Distribution Unlimited



## Advanced Solid State Lasers

19960723 039


DTIC QUALITY INSPECTED 3

OSA

Optical Society of America

Edited by Stephen A. Payne and Clifford R. Pollock

# DISCLAIMER NOTICE



THIS DOCUMENT IS BEST QUALITY AVAILABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.

Articles in this publication may be cited in other publications. In order to facilitate access to the original publication source, the following form for the citation is suggested:

Name of Author(s), Title of Paper, OSA Trends in Optics and Photonics on Advanced Solid State Lasers, Stephen A. Payne and Clifford R. Pollock, eds. (Optical Society of America, Washington, DC 1996), Vol. 1, pp. xx-xx.

Cover photo: Courtesy of Lawrence Livermore National Laboratory. See paper on page 208.

ISBN Number 1-55752-370-3

LC Number 95-71001

Copyright © 1996, Optical Society of America

Individual readers of this publication and libraries acting for them are permitted to make fair use of the material in it, as defined by Sections 107 and 108 of the U.S. Copyright Law, such as to copy an article for use in teaching or research, without payment of fee, provided that such copies are not sold. Copying for sale or copying for use that exceeds fair use as defined by the Copyright Law is subject to payment of copying fees. The code 1-55752-370-3/96/\$10.00 gives the per-article copying fee for each copy of the article made beyond the free copying permitted under Sections 107 and 108 of the U.S. Copyright Law. The fee should be paid through the Copyright Clearance Center, Inc., 21 Congress Street, Salem, MA 01970.

Permission is granted to quote excerpts from articles in this publication in scientific works with the customary acknowledgment of the source, including the author's name, name of the publication, page, year, and name of the Society. Reproduction of figures and tables is likewise permitted in other articles and books provided that the same information is printed with them, and notification is given to the Optical Society of America. Republication or systematic or multiple reproduction of any material in this proceedings, including contents and abstracts, is permitted only under license from the Optical Society of America; in addition, the Optical Society may require that permission also be obtained from one of the authors. Electrocopying or electrostorage of any material in this publication is strictly prohibited. Address inquiries and notices to the Director of Publications, Optical Society of America, 2010 Massachusetts Avenue, NW, Washington, DC 20036. In the case of articles whose authors are employees of the United States Government or its contractors or grantees, the Optical Society of America recognizes the right of the United States Government to retain a nonexclusive, royalty-free license to use the author's copyrighted article for United States Government purposes.

The views and conclusions contained in this publication are those of the author(s) and should not be interpreted as necessarily representing endorsements, either expressed or implied, of the editors or the Optical Society of America.

Printed in the U.S.A.

# Stimulated emission without cavity in powders and single crystals of Nd doped materials

M. A. Noginov\*, N. E. Noginova, H. J. Caulfield\*\*, P. Venkateswarlu\*,  
T. Thompson, M. Mahdi.

\*Center for Nonlinear Optics and Materials, \*\*Center for Applied Optical Science, Department of Physics,  
Alabama A&M University, P. O. Box. 1268,  
Normal, AL 35762.

V. Ostroumov.

Institute of Laser Physics, Hamburg University, Jungiusstrasse 9-11, D 20355, Hamburg, Germany.

## Abstract

Short ( $>300$  ps) pulses of stimulated emission were found from powders of  $\text{NdAl}_3(\text{BO}_3)_4$ ,  $\text{NdSc}_3(\text{BO}_3)_4$ , and  $\text{Nd}:\text{Sr}_2(\text{PO}_4)_3\text{F}$  laser crystals under 532 nm and 805 nm excitation. Study of stimulated emission in the mixture of two powders has shown that different components influenced each other. The main features of experimentally observed stimulated emission are described with a simple model accounting for  $^4\text{F}_{3/2}$  excited state concentration and emission energy density.

## Key Words

Rare earth and transition metal solid-state lasers (432); Laser theory (86); Scattering by particles (2157); Microstructure devices (454).

## Introduction

In 1986 Markushev *et al.*<sup>1</sup> showed that a powder of  $\text{Na}_3\text{La}_{1-x}\text{Nd}_x(\text{MoO}_4)_4$  at liquid nitrogen temperature pumped at  $\lambda=575\text{--}590$  nm exhibited a laser-like behavior without an external cavity. After some threshold pump energy, the Nd emission spectrum narrowed to a single intense line and short emission pulses appeared in response to a 30 ns Q-switched laser pulse. In succeeding papers by the same group<sup>2-4</sup> the spectral and temporal behaviors of the emission pulses were studied in more detail in various Nd doped crystals. Laser-like behavior of Nd emission in polycrystals of  $\text{Nd}_x\text{La}_{1-x}\text{P}_3\text{O}_{14}$  and powders of  $(\text{NdCl}_3 \cdot 6\text{H}_2\text{O})$  was first demonstrated in Ref. 5 at room temperature. In the same work emission pulses above the threshold were found to be of low coherence.

The short-spike formation and narrowing of the emission spectrum is thought to be due to collective behavior of many particles, where emission is amplified

in the gain medium. The diffusion of photons in gain scattering medium was studied by Letokhov in Ref. 6. However, a detailed explanation of the phenomenon is not currently available in the literature.

From the practical point of view, the study of laser-like emission in powders is very interesting because of potential applications of compact, low-cost, and very simply designed lasers based on powders of laser crystals, which do not need any mirrors and adjustment.

## Experimental measurements

In the experiment, we studied powders of the  $\text{NdAl}_3(\text{BO}_3)_4$ ,  $\text{NdSc}_3(\text{BO}_3)_4$ , and  $\text{Nd}(2\%):\text{Sr}_2(\text{PO}_4)_3\text{F}$  (Nd:S-FAP) laser crystals. An average size of the powder particles was approximately equal to 5  $\mu\text{m}$ . The samples were pumped with Q-switched frequency doubled Nd:YAG laser or 805 nm Cr:LiCAF laser.

Experimentally we analyzed spectra and kinetics of Nd emission at low and high pumping densities. All experiments were carried out at room temperature. We found that, after the pump energy exceeds some threshold value, both the kinetics and the spectra of Nd luminescence change very dramatically. Above the threshold, the luminescence spectrum narrows down to a single line, the measured value of the full width at half height (FWHH) equal to 2 Å was limited by the monochromator. Figure 1 shows the transformation of the spectrum in the  $\text{NdAl}_3(\text{BO}_3)_4$  powder with increase of pumping intensity. The spectrally narrow light was emitted in one or several short pulses. In  $\text{NdAl}_3(\text{BO}_3)_4$ , the duration of the pulses varied from  $\sim 300$  ps to  $\sim 1.3$  ns (Fig. 2). The other materials studied demonstrated similar behavior. As is typical for most lasers, the dependence of the stimulated emission intensity from the powder on the pump energy is as presented in Fig. 3.




Figure 1. Emission spectrum of  $\text{NdAl}_3(\text{BO}_3)_4$  powder a) below the threshold ( $\approx 30 \text{ mJ/cm}^2$ ) and b) above the threshold ( $\approx 240 \text{ mJ/cm}^2$ ),  $\lambda = 1063.1 \text{ nm}$ .

The threshold energy density, the threshold Nd excited state concentration, and the threshold gain at the  ${}^4\text{F}_{3/2} \rightarrow {}^4\text{I}_{11/2}$  transition in the three powder samples studied are summarized in Table 1. The energy levels diagram of  $\text{Nd}^{3+}$  ions is presented in Fig. 4.

An apparently similar emission behavior we observed under pulsed Ti-sapphire pumping (808 nm, 20 ns) in polished plane-parallel samples of  $\text{Nd:GVO}_4$




Figure 2. Pulses of stimulated emission from  $\text{NdAl}_3(\text{BO}_3)_4$  powder 1) near the threshold ( $200 \text{ mJ/cm}^2$ ), 2) at  $x=1.6$  times threshold energy, 3)  $x=1.9$ , 4)  $x=3.9$ .




Figure 3. Experimental dependence of the intensity of stimulated emission in  $\text{NdAl}_3(\text{BO}_3)_4$  on the pump energy,  $\lambda = 1063.1 \text{ nm}$ .

( $\text{Nd}=0.9\%$ ,  $2.8\%$ ) and  $\text{Nd}_x\text{La}_{1-x}\text{Sc}_3(\text{BO}_3)_4$  ( $x=0.1, 0.25$ ). Short and very intense emission spikes were observed in both materials when Ti-sapphire laser was tuned to the maximum of Nd absorption. In both crystals the ratio of the spike intensity to the intensity of the succeeding "regular" luminescence was approximately equal to  $10^4$ . Above the threshold, the dependence of spike intensity on pump energy was practically linear.

	$\text{NdAl}_3(\text{BO}_3)_4$	$\text{NdSc}_3(\text{BO}_3)_4 / \text{Nd}_x\text{La}_{1-x}\text{Sc}_3(\text{BO}_3)_4$	Nd:S-FAP
Nd concentration in 100% doped sample	$5.3 \times 10^{21} \text{ cm}^{-3}$ , Ref. 7	$5.1 \times 10^{21} \text{ cm}^{-3}$ in $\text{NdSc}_3(\text{BO}_3)_4$ , Refs. 8,9	$1.68 \times 10^{22} \text{ cm}^{-3}$ , Ref. 10
$^4\text{F}_{3/2}$ life-time	20 $\mu\text{s}$ , Ref. 7	Nd(1-10%): $\text{LaSc}_3(\text{BO}_3)_4$ 118 $\mu\text{s}$ $\text{NdSc}_3(\text{BO}_3)_4$ 24 $\mu\text{s}$ , Refs. 8,9	298 $\mu\text{s}$ , Ref. 10
Wavelength of the maximum emission cross section	$\approx 1.063 \mu\text{m}$ Ref. 11	1.0615 $\mu\text{m}$ , (our measurements)	1.059 $\mu\text{m}$ , Refs. 10,12
$^4\text{F}_{3/2} - ^4\text{I}_{11/2}$ emission cross section	$10 \times 10^{-19} \text{ cm}^2$ , Ref. 7	$\text{Nd}_{0.1}\text{La}_{0.9}\text{Sc}_3(\text{BO}_3)_4$ Ellx, $13 \times 10^{-20} \text{ cm}^2$ , Elly, $9 \times 10^{-20} \text{ cm}^2$ , Ellz, $5 \times 10^{-20} \text{ cm}^2$ , Ref. 8, averaged over different polarizations: $9 \times 10^{-20} \text{ cm}^2$	Ellc, $5.4 \times 10^{-19} \text{ cm}^2$ , Elc, $2.4 \times 10^{-19} \text{ cm}^2$ , Refs. 10,12, averaged over different polarizations: $3.9 \times 10^{-19} \text{ cm}^2$
Absorption cross section at the pump wavelength	Ellc $3.3 \times 10^{-21} \text{ cm}^2$ , Elc, $2.6 \times 10^{-21} \text{ cm}^2$ , ( $\lambda = 532 \text{ nm}$ ); Ref. 13	Ellx, $5.1 \times 10^{-21} \text{ cm}^2$ , Elly, $4.2 \times 10^{-21} \text{ cm}^2$ , Ellz, $2.4 \times 10^{-21} \text{ cm}^2$ , ( $\lambda = 532 \text{ nm}$ ); Ref. 14	Ellc, $2.26 \times 10^{-19} \text{ cm}^2$ , Elc, $0.7 \times 10^{-19} \text{ cm}^2$ , ( $\lambda = 805 \text{ nm}$ ); Ref. 10
Absorption coefficient of the powder (averaged over different polarizations)	$\approx 15 \text{ cm}^{-1}$ ( $\lambda = 532 \text{ nm}$ , 100% Nd)	$\approx 20 \text{ cm}^{-1}$ ( $\lambda = 532 \text{ nm}$ , 100% Nd)	$\approx 55 \text{ cm}^{-1}$ ( $\lambda = 805 \text{ nm}$ , 2% Nd)
Threshold pump density (in the powder)	200 $\text{mJ/cm}^2$ ( $\lambda = 532 \text{ nm}$ )	560 $\text{mJ/cm}^2$ ( $\lambda = 532 \text{ nm}$ )	170 $\text{mJ/cm}^2$ ( $\lambda = 805 \text{ nm}$ )
Threshold Nd excited state concentration	$7.5 \times 10^{18} \text{ cm}^{-3}$	$2.8 \times 10^{19} \text{ cm}^{-3}$	$3.64 \times 10^{19} \text{ cm}^{-3}$
Threshold gain	$\approx 7.5 \text{ cm}^{-1}$	$\approx 2.5 \text{ cm}^{-1}$	$\approx 15.7 \text{ cm}^{-1}$

Table 1. Spectroscopic data on  $\text{NdAl}_3(\text{BO}_3)_4$ ,  $\text{Nd}_x\text{La}_{1-x}\text{Sc}_3(\text{BO}_3)_4$ , and Nd:S-FAP laser crystals. (In  $\text{Nd}_x\text{La}_{1-x}\text{Sc}_3(\text{BO}_3)_4$  the most of data are available on low Nd doped crystals. The change of the crystal symmetry at >50% Nd concentration may influence some of spectroscopic parameters.)

Similar laser-like effects in the emission from small single crystals of  $\text{NdAl}_3(\text{BO}_3)_4$  were reported in Ref. 7.

To compare the behavior of spiked emission from powders to that from single crystals, we studied polished and unpolished plates of the Nd(2%):S-FAP single crystals, and small ( $\approx 1 \text{ mm}^3$ ) single crystals of  $\text{NdAl}_3(\text{BO}_3)_4$  and  $\text{NdSc}_3(\text{BO}_3)_4$  (Table 2); we also studied a thin layer of  $\text{NdAl}_3(\text{BO}_3)_4$  powder. As follows from Table 2, three factors help stimulated emission to occur: 1) appreciably large pumped

volume, 2) preparation of the material in the powder form (scattering), and 3) polished plane-parallel surfaces in the bulk crystals (feedback). (Note, that the last result is different from that of Ref. 15, where the reflections off the cell walls did not decrease but increased the threshold in the dye+powder gain scattering medium).

To determine the portion of the energy stored at the level  $^4\text{F}_{3/2}$  went to the stimulated emission channel, we studied a) the kinetics of luminescence at the  $^4\text{F}_{3/2} \rightarrow ^4\text{I}_{9/2}$  transition during the stimulated emission pulses, b)

	NdAl <sub>3</sub> (BO <sub>3</sub> ) <sub>4</sub> $\lambda_{\text{pump}}=532 \text{ nm}$		NdSc <sub>3</sub> (BO <sub>3</sub> ) <sub>4</sub> $\lambda_{\text{pump}}=532 \text{ nm}$	Nd:S-FAP $\lambda_{\text{pump}}=805 \text{ nm}$	
Powders	$V \geq 1 \text{ mm}^3$	200 mJ/cm <sup>2</sup>	560 mJ/cm <sup>2</sup> ( $V \geq 1 \text{ mm}^3$ )	170 mJ/cm <sup>2</sup> ( $V \geq 1 \text{ mm}^3$ )	
	thin monolayer of powder	at $\leq 1 \text{ J/cm}^2$ threshold was not achieved	—	—	
Single crystals	$V=1 \text{ mm}^3$	600 mJ/cm <sup>2</sup>	—	8 mm polished plate	625 mJ/cm <sup>2</sup>
				1.5 mm polished plate	920 mJ/cm <sup>2</sup>
				0.8 mm unpolished plate	1080 mJ/cm <sup>2</sup>

Table 2. Thresholds of the stimulated emission in the powders and single crystals of NdAl<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub>, Nd<sub>x</sub>La<sub>1-x</sub>Sc<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub>, and Nd:S-FAP laser crystals.




Figure 4. Nd<sup>3+</sup> energy levels diagram, excitation and relaxation processes in Nd<sup>3+</sup>: 1) - pumping, 2) - multiphonon relaxation populating the metastable level <sup>4</sup>F<sub>3/2</sub>, 3) radiation and multiphonon relaxation of the level <sup>4</sup>F<sub>3/2</sub>, 4) stimulated emission at the transition <sup>4</sup>F<sub>3/2</sub> → <sup>4</sup>I<sub>9/2</sub>, 5) cross relaxation.

analyzed the dependence of the peak <sup>4</sup>F<sub>3/2</sub> → <sup>4</sup>I<sub>9/2</sub> emission vs pump energy, and c) compared the area under the stimulated emission pulses and residual spontaneous emission kinetics from the level <sup>4</sup>F<sub>3/2</sub>. Combining the results of the three measurements above, we estimated the quantum yield of stimulated emission to be rather small, ≈0.2%, at the pump energy two times greater than the threshold energy. However, accounting for the small pulse duration of the stimulated emission, the peak power of the stimulated emission was comparable to that of the pump pulses.

We then turned to the study of mixtures of the two powders. We tried ≈1/6 NdAl<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub> and ≈5/6 NdSc<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub>, by volume. In the mixtures, the maximum strong luminescence line of NdAl<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub>




Figure 5. Image of stimulated emission from the mixture of ≈1/6 NdAl<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub> and ≈5/6 NdSc<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub> as it appears on the screen of streak camera connected to monochromator

( $\lambda=1063.1 \text{ nm}$ ) was practically not seen under the relatively wide line of NdSc<sub>3</sub>(BO<sub>3</sub>)<sub>4</sub>. Above the threshold, however, two narrow emission lines (1063.1 nm and 1061.5 nm) appeared. Their thresholds and relative strengths were strongly dependent on very small variations of concentrations of the components.

Combining the streak camera with the monochromator, we obtained a three-dimensional picture (wavelength-time-intensity) of the stimulated emission in the mixture of two powders, Fig. 5. When the pump energy was above the threshold required for both lines, several short pulses of emission appeared at 1063.1 nm, after that emission jumped to 1061.5 nm which gave one or several short pulses, depending on the pump energy.

In a one-component medium the first pulse in the series was always the strongest one, Fig. 2. In contrast, in the mixture of two powders (see Fig. 5), where the first pulse in 1061.5 nm series coincided in time with the last pulse in 1063.1 nm series, the first 1061.5 nm pulse was strongly damped and weaker than succeeding




Figure 6. Calculated according to Eq. (1) dynamics of stimulated emission (a, c, e) and  ${}^4F_{3/2}$  excited state concentration (b, d, e) in  $\text{NdAl}_3(\text{BO}_3)_4$ . Pumping density:  $1000 \text{ mJ/cm}^2$  in a,b,  $400 \text{ mJ/cm}^2$  in c,d, and  $200 \text{ mJ/cm}^2$  (the threshold) in f,e. Dashed line - pump pulse.

pulses of the same series. From this observation we conclude that in the mixture individual components do not operate independently. This also implies that in one-component medium many particles behave collectively to produce stimulated emission pulses.

#### Comparison of experiment and theory. Discussion

The threshold behavior of stimulated emission and the short emission pulses we describe by a simple model accounting for the Nd excited state concentration,  $n$ , and emission energy density,  $E$ , in the pumped volume:

$$\begin{aligned} \frac{dn}{dt} &= \frac{K(t)N\sigma_{\text{abs}}}{h\nu_{\text{pump}}} - \frac{n}{\tau_1} - \beta nN - \frac{E}{h\nu_{\text{em}}} \sigma_{\text{em}} n \\ \frac{dE}{dt} &= -\frac{E}{\tau_2} + \frac{n}{\tau_1} h\nu_{\text{em}} + E\sigma_{\text{em}} n \end{aligned} \quad (1)$$

Here  $K(t)$  is the pump power density,  $N$  is the ground state concentration of Nd,  $\sigma_{\text{abs}}$  is the absorption cross section at the pump wavelength,  $\sigma_{\text{em}}$  is the emission cross section at the wavelength of stimulated emission,  $h\nu_{\text{pump}}$  is the photon energy at the pump wavelength,  $h\nu_{\text{em}}$  is the photon energy at the emission wavelength,  $\tau_1$  is the life-time of the level  ${}^4F_{3/2}$ ,  $\beta N$  is the rate of cross relaxation,  $\tau_2$  is the effective life-time of the photon in the pumped volume,  $c$  is the speed of light.

The idea behind Eq. (1) (to watch for dynamics of emission energy in the pumped volume) is close to that of Letokhov<sup>6</sup> who calculated threshold for stimulated emission in the gain scattering medium. Equation (1) is also similar to that for laser relaxation oscillations, where  $\tau_2$  has a meaning of the photon life-time in the laser cavity.

In the numerical solution of Eq. (1) we used the spectroscopic parameters close to that in the  $\text{NdAl}_3(\text{BO}_3)_4$  experiment. The only unknown parameter in Eq. (1) was  $\tau_2$ , the effective photon life-time in the pumped volume. We used it as an adjustable parameter



to fit the experimental energy threshold and found  $\tau_2=10$  ps. At  $n'=1.5$  this value of  $\tau_2$  corresponds to the average 2 mm photon path in the pumped medium. This seems to be a reasonable value for  $\approx 1$  mm pump beam cross section and  $\approx 0.7$  mm absorption length (in  $\text{NdAl}_3(\text{BO}_3)_4$ ) in our experiment.

The calculated dynamics of emission energy density and  ${}^4\text{F}_{3/2}$  excited state concentration are shown in Fig. 6. The appearance of calculated emission pulses is very close to that observed experimentally. The analysis of excited state concentration dynamics,  $n(t)$ , shows that pulses of stimulated emission occur when  $n$  exceeds some critical threshold value, practically independent of pump density.

We have shown that the calculated threshold of stimulated emission is inversely proportional to the absorption coefficient at the pump wavelength,  $k_{\text{abs}}=N\sigma_{\text{abs}}$  (pump efficiency), emission cross section,  $\sigma_{\text{em}}$ , and escape-time of photon from the pumped volume,  $\tau_2$  (photon walk length in the pumped volume). Thus, the threshold is inversely proportional to the small signal amplification along the effective photon path in the pumped volume. This result is in an agreement with our experimental observations. For lasers the described threshold behavior is obvious and have been demonstrated elsewhere.

According to our simple model, preparation of the sample in powder form and polishing of surfaces do not produce any special condition necessary for stimulated emission to occur, but only reduce the threshold of stimulated emission. Short pulses of stimulated emission are predicted (and obtained experimentally) at higher but still reasonable pumping energy in excited crystal without any scattering and reflection feedback.

## Summary

Room temperature stimulated emission was found in the powders of  $\text{NdAl}_3(\text{BO}_3)_4$ ,  $\text{NdSc}_3(\text{BO}_3)_4$ , and Nd:SFAP laser crystals under Q-switched laser pumping: when the pump energy exceeded the threshold value, Nd emission spectrum narrowed to a single line, one or several short ( $>300$  ps) emission pulses appeared in response to the pump pulse.

Similar behavior, but at higher thresholds, was found in single crystals of the same materials. However, no stimulated emission was obtained in a monolayer of powder. Thus, appreciably large pumped volume and long paths of emission photons help to reduce the threshold of stimulated emission. It was shown that only small portion of excitation stored at the  ${}^4\text{F}_{3/2}$  Nd level goes to the stimulated emission channel.

Study of stimulated emission in the mixture of two powders has shown that different components influence each other, that implies a collective behavior of many emitting particles.

The main features of the experimentally observed short pulsed emission were described with a simple

model accounting for the  ${}^4\text{F}_{3/2}$  excited state concentration and emission energy density in the pumped volume.

## Acknowledgments

The work was done under the support of the MRCE-NSF grant #HRD-9353548, ARO Grant #DAA L 03-91-G-0316, and (for H. J. C.) the Air Force Office of Scientific Research. Authors acknowledge the help of Ms. C. Cochrane for the microscope photographs of the powders. The  $\text{NdAl}_3(\text{BO}_3)_4$  and  $\text{NdSc}_3(\text{BO}_3)_4$  crystals used in the experiments were kindly provided by Prof. G. Huber of Hamburg University, Germany. We thank Prof. G. Huber for his collaboration. We also acknowledge the assistance of Prof. M. Bass and Dr. X. X. Zhang of CREOL at the University of Central Florida in conducting the Nd:SFAP related experiments.

## References

1. V. M. Markushev, *et al.*, Sov. J. Quantum Electronics, **16**, pp. 281-283 (1986).
2. V. M. Markushev, *et al.*, Sov. J. Quantum Electron., **20**, pp. 773 - 777 (1990).
3. N. É. Ter-Gabriélyan, *et al.*, Sov. J Quantum Electron., **21**, pp. 840-842 (1991).
4. N. É. Ter-Gabriélyan, *et al.*, Sov. J. Quantum Electron., **21**, pp. 32-33 (1991).
5. C. Guedard, *et al.*, J. Opt. Soc. Am. B, **10**, pp. 2358-2363.
6. V. S. Letokhov, Soviet Physics JETP, **26**, pp. 835-840 (1968).
7. G. Huber, "Miniature neodymium lasers", in the book Current Topics in Materials Science, Vol. **4**, E. Kaldis, editor, North-Holland, 1980, pp. 1-45.
8. J.-P. Mein, *et al.*, IEEE Journal Quant. Electron., **30**, pp. 913-917 (1994).
9. V. Ostroumov, *et al.*, OSA Proceeding on Advanced Solid-State Lasers, (OSA, Washington, DC 1995), Vol. **24**, pp. 509-513.
10. X. X. Zhang, *et al.*, Appl. Phys. Lett., **64**, pp. 3205-3207 (1994).
11. G. Huber, H. G. Danielmeyer, Appl. Phys., **18**, pp. 77-80 (1979).
12. X. X. Zhang, *et al.*, OSA Proceeding on Advanced Solid-State Lasers, (OSA, Washington, DC 1995), Vol. **24**, pp. 150-152.
13. H.-D. Hattendorf, Dissertation zur Erlangung des Doktorgrades des Fachbereich Physik der Universität Hamburg, Hamburg, 1979, 97 p.
14. J.-P. Meyn, Dissertation zur Erlangung des Doktorgrades des Fachbereich Physik der Universität Hamburg, Hamburg, 1994, 115 p.
15. Balachandran, N. M. Lawandy, Opt. Lett, **20**, pp. 1271-1273 (1995).